


## Electro-Optic DSTMS Crystals

4-N,N-dimethylamino-4'-N'-methyl-stilbazolium 2,4,6-trimethylbenzenesulfonate



### Properties

- high quality crystals
- cut and polished for various applications
- large nonlinear optical susceptibilities
- large electro-optic coefficients
- phase matching for THz-wave generation between 720 nm and 1650 nm


### Applications

- efficient THz generation and detection from 0.3 to >16 THz
- fast electro-optic modulation
- optical parametric generation
- efficient frequency doubling of 1.55  $\mu\text{m}$  radiation


## Physical Properties

melting temperature	250 °C		
point group symmetry	m		
refractive indices @ 1550 nm	$n_1$	=	2.07, $n_2 = 1.64$
nonlinear optical coefficients @ 1900 nm	$d_{111}$	=	$214 \pm 20$ pm/V
	$d_{122}$	=	$31 \pm 4$ pm/V
	$d_{212}$	=	$35 \pm 4$ pm/V
electro optic coefficient @ 1900 nm	$r_{111}$	=	$37 \pm 3$ pm/V

## Absorption Spectrum



## THz Conversion Efficiency



- 1) "Large-Size Bulk and Thin-Film Stilbazolium-Salt Single Crystals for Nonlinear Optics and THz Generation"; Z. Yang, L. Mutter, M. Stillhart, B. Ruiz, S. Aravazhi, M. Jazbinsek, A. Schneider, V. Gramlich and P. Günter, Adv. Funct. Mater. 17, 2018 (2007).
- 2) "Large-Size Bulk and Thin-Film Stilbazolium-Salt Single Crystals for Nonlinear Optics and THz Generation"; Z. Yang, L. Mutter, M. Stillhart, B. Ruiz, S. Aravazhi, M. Jazbinsek, A. Schneider, V. Gramlich and P. Günter, Adv. Funct. Mater. 17, 2018 (2007).
- 3) "Linear and nonlinear optical properties of the organic crystal DSTMS"; L. Mutter, F. Bruner, Z. Yang, M. Jazbinsek, P. Günter, J. Opt. Soc. Am. B 24, 2556 (2007).
- 4) "Molecular engineering of stilbazolium derivatives for second-order nonlinear optics": Z. Yang, M. Jazbinsek, B. Ruiz, S. Aravazhi, V. Gramlich, P. Günter, Chem. Mater. 19, 3512-3518 (2007).

## Rainbow Photonics AG

Farbhofstrasse 21  
CH-8048 Zürich

Phone: +41 44 419 05 05  
Fax: +41 44 419 05 06  
E-mail: info@rainbowphotonics.com  
Web: www.rainbowphotonics.com

